


RUSTEND® FISH OIL COMPOUND

RUSTEND® Fish Oil Compound is a special purpose high-penetration, corrosion inhibiting coating that cures to leave a clear pale straw film. The product is lead free.

MAIN CHARACTERISTICS

| | |
|---------------------|--|
| Areas of Use | The product is formulated to be used in areas where access to a metal surface is difficult. RUSTEND® Fish Oil Compound penetrates deeply through microscopic cracks and fissures in the metal surface and dries to a solid film inhibiting further corrosion. |
| Features | <ul style="list-style-type: none">• Rust preventative coating• Heavy duty formula ideal for use on new or rusted metal surfaces• Very low odour• Suitable for use in automotive, industrial, marine & household applications• Easy to use• Capability to penetrate and protect inaccessible rust prone areas such as joints, cracks, side panels, sills and other metal areas |
| Properties | Finish: Clear, pale straw coloured Weight Solids: 57% minimum (w/w) Volume Solids: 61% Theoretical Spreading Rate: 12–16 m ² /L/coat Wet Film Thickness: 65–100 µm WFT per coat Dry Film Thickness: 40–60 µm DFT per coat Specific Gravity: 0.91 kg/L @ 25°C Chemical Resistance: Excellent chemical and alkali resistance Odour: Very low odour VOC: 378 g/L Appearance: Clear, pale straw coloured Appearance when dry: Clear gloss The values listed are typical values and should not be interpreted as specifications. |
| Coverage | Surface type and texture affects the coverage rate. Generally, the recommended spreading rate is 12–16 m ² /L/coat. |
| Precautions | Obtain 24 hour weather forecast. |

| | | | | | | | | | | | | | |
|----------------------------|---|----------------------------|--------------|--------------|--------------|----------------------|--------|--------|--------|-----------------------|------------|------------|------------|
| | <p>Do NOT apply RUSTEND® Fish Oil Compound:</p> <ul style="list-style-type: none"> I. If the surface or ambient temperature is above 35 °C or likely to be so during the drying period (at an air temperature of 35 °C, it would not be unusual to have a surface temperature of >50 °C) II. If the ambient temperature is below 5 °C, III. If the surface temperature is below 5 °C, IV. If minimum temperature is forecast to be below 5 °C within 24 hours of application V. Do not apply if the relative humidity is above 85% or the surface temperature is less than 3 °C above dewpoint VI. Avoid painting in direct sunlight on hot days VII. Do not use in areas where extended ponding is likely to occur VIII. Do not apply a heavy film, as this can result in solvent entrapment and wrinkling. <p>All personnel participating in application must use appropriate personal protective equipment (PPE) to prevent contact with skin, eyes and breathing of vapours. A sun hat and sunscreen are also recommended if applying outdoors.</p> | | | | | | | | | | | | |
| Application | <p>Preparation and application instructions can be found at colormaker.com.au</p> <div style="text-align: right;">  </div> <p>Scan for RUSTEND® Fish Oil Compound Application Guide</p> | | | | | | | | | | | | |
| Dry Times | <p>Touch dry in 8 hours at 25 °C and 50% RH. Allow longer drying time in cooler and more humid conditions.</p> <table border="0"> <tr> <td>Drying Temperature:</td> <td>15 °C</td> <td>25 °C</td> <td>35 °C</td> </tr> <tr> <td>Minimum Recoat Time:</td> <td>24 hrs</td> <td>16 hrs</td> <td>16 hrs</td> </tr> <tr> <td>Maximum Recoat Time*:</td> <td>Open ended</td> <td>Open ended</td> <td>Open ended</td> </tr> </table> <p>Hard Cure: 7 days (at 25 °C and 50% R.H.)</p> <p>*Best within 48 hours to minimise impact of airborne and other contaminants</p> | Drying Temperature: | 15 °C | 25 °C | 35 °C | Minimum Recoat Time: | 24 hrs | 16 hrs | 16 hrs | Maximum Recoat Time*: | Open ended | Open ended | Open ended |
| Drying Temperature: | 15 °C | 25 °C | 35 °C | | | | | | | | | | |
| Minimum Recoat Time: | 24 hrs | 16 hrs | 16 hrs | | | | | | | | | | |
| Maximum Recoat Time*: | Open ended | Open ended | Open ended | | | | | | | | | | |
| Clean Up | Clean all equipment while still wet with mineral turpentine. | | | | | | | | | | | | |
| Colour range | Clear pale straw colour | | | | | | | | | | | | |
| Packaging | Available in 4 L and 1 L steel cans. Reseal containers immediately after use. | | | | | | | | | | | | |

| | |
|----------------------------|---|
| Shelf Life | Store in a cool, dry place in sealed containers. Shelf life before opening is 24 months. Reseal containers immediately after use. Once opened and resealed, ideally use the remaining contents within 6 months. |
| Health & Safety | <p>Thoroughly read the SDS before commencing any application.</p> <p>Keep out of reach of children. Avoid inhalation, breathing vapour and contact with skin.</p> <p>Wear adequate personal protection when mixing or applying.</p> <p>Always provide adequate ventilation, especially in confined areas.</p> <p>If swallowed, immediately rinse mouth and then drink plenty of water. Do NOT induce vomiting. Immediately call a Poisons Information Centre 13 11 26 or a doctor.</p> <p>In the event of paint splash on the skin remove/take off immediately all contaminated clothing. Rinse skin with water/shower. If irritation occurs seek medical advice.</p> <p>If the event of eye contact immediately wash with plenty of fresh water for at least 15 minutes. Hold eyelids open. In all cases of eye contamination, it is a sensible precaution to seek medical advice.</p> <p>In the event of a spill, control the spread of paint to prevent contamination of drains and waterways. Clean up spills with absorbent materials such as soil, sand, or inert material, then collect and seal in properly labelled containers for disposal.</p> |
| Ancillary Products | <p>RUSTEND® Galvanised Iron Primer</p> <p>RUSTEND® Zinc Phosphate Anti-Corrosive Primers</p> <p>RUSTEND® Silver Enamel</p> |

STATEMENT OF RESPONSIBILITY: The technical and/or application advice offered in this publication represents the present state of our knowledge and is believed to be reliable. Buyers and intended users of all Colormaker Industries products should read the product label, TDS and Application Guide carefully and then conduct their own assessment to confirm the suitability of the product, including in conjunction with other products and the types of surfaces to, and the manner in which, the product will be applied. This is to satisfy themselves that the product is suitable for use in the area intended and under conditions of application and cure. Given the wide range of substrates, environmental conditions and methods of application, Colormaker Industries offers no warranty of performance, either expressed or implied based on the above information. The painter, contractor or applicator of Colormaker Industries products may reject the advice given by Colormaker Industries either orally or in writing as it is their responsibility, not that of Colormaker Industries, to carry out appropriate application within any given context.

RUSTEND® is a registered trademark

© Colormaker Industries 2023

v230105v1j